

Metallic paint



Description A general purpose metallic silver finish for interior or exterior exposure on many types of substrate.

Recommended Use Suitable for application by brushing or spraying to clean bare steel, or appropriately primed surfaces.

Also suitable for use as a sealer on surfaces having a moderate coat of bituminous material applied, or as a substitute for shellac knotting.

Gives excellent heat resistance from cold up to 200°C.

Compliance Complies with "the VOC in Paints, Varnishes & Vehicle Refinishing Products Regulations 2005". EU limit value for this product, (cat A/i): 500g / litre (2010)

Recommended Application Methods Conventional spray. Airless spray. Brush.

Colour Range Silver

Physical Properties
VOC Content (as supplied) : max 490g / litre
Volume Solids : 50%
Mass Solids : 48%
Flash Point : 38°C

Drying Time @ 20°C Surface dry - 3 hours. Hard dry - 8 hours. Overcoat after 16 hours. Drying times will be extended at low temperatures. Do not apply when ambient temperature falls below 5°C or relative humidity exceeds 90%.

Dry Film Thickness 15 - 30 µ

Wet Film Thickness 30 - 60 µ

Theoretical Coverage Rate 20m² per litre @ 25µ DFT
Coverage rate can be affected by such variables as type and condition of substrate, type of application equipment and individual method of application.

Thinners Firwood 114 Low Odour Thinners

Packaging
Pack Size : 5 litres
Weight : 0.95kg / litre
Shelf Life : 2 years from shipment date when stored in unopened, original containers.
Storage : Store in temperature range 5-40°C

Directions for use	All surfaces should be clean, dry and free from grease, rust, millscale, etc. For optimum performance of this product, it should be applied over carefully prepared surfaces. The most effective method is by blast cleaning to Swedish Standard Sa2½ and recoated within 4 hours. If this is not practical, then the surface should be mechanically cleaned using wire brushes, scrapers, etc. For further information contact our Technical Service Department.
Cleaning	Application equipment should be cleaned using Firwood 114 Low Odour Thinners
Health & Safety	Refer to Material Safety Data Sheet for information on correct handling and application of this product.



The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use.

Firwood Paints Ltd. Oakenbottom Road, Bolton, UK, BL2 6DP

T. +44 (0)1204 525231 **F.** +44 (0)1204 362522 **E.** sales@firwood.co.uk **W.** www.firwood.co.uk

Registered in England No.: 207861 Registered office: Oakenbottom Road, Bolton, BL2 6DP

Data sheet Ref 195/1
Date of issue 03/11/14