

## One coat wall paint



<b>Description</b>	A fast drying, water borne acrylic wall paint for application by airless spray or roller. Quick and easy to apply with good obliterating power and brightness. Good resistance to splashes of petrol, diesel, oil and water. Acts as a primer sealer on both new and previously painted walls and ceilings.
<b>Recommended Use</b>	Suitable for use on brickwork, rendered walls, breeze block and concrete. Surface to be painted should be dry and free from dust and other contaminants. Always allow recently rendered walls to fully cure before painting.
<b>Compliance</b>	Complies with "the VOC in Paints, Varnishes & Vehicle Refinishing Products Regulations 2005". EU limit value for this product (cat A/a): 30g / litre (2010)
<b>Recommended Application Methods</b>	Methods Airless spray Brush Roller
<b>Colour Range</b>	White. Other shades to order
<b>Physical Properties</b>	<u>VOC Content</u> (as supplied) : max 30g / litre <u>Volume Solids</u> : 38% <u>Mass Solids</u> : 59% <u>Flash Point</u> : n/a
<b>Drying Time @ 20°C</b>	The product will normally be touch dry in 30 mins and can be overcoated after 24 hours. It is advisable not to apply the product when the ambient temperature falls below 10°C or the relative humidity exceeds 85%. Keep coated areas dry for a minimum of 24 hours following application. Coverage will vary dependent on the absorbency of the substrate
<b>Theoretical Coverage Rate</b>	7.5 sq m per litre @ 75µ micron DFT. Approx 130µ WFT Coverage rate can be affected by such variables as type and condition of substrate, type of application equipment and individual method of application.
<b>Thinners</b>	Use clean cold water.
<b>Packaging</b>	<u>Pack Size</u> : 5 litre tins. <u>Weight</u> : 1.3 - 1.5kg / litre (dependant on colour) <u>Shelf Life</u> : 12 months from shipment date when stored in unopened, original containers. <u>Storage</u> : Store in temperature range 5-40°C

---

<b>Surface Preparation - Bare Concrete</b>	Surfaces to be coated should be at least 4 weeks old and have a moisture content of less than 7%. They should also be free from any contaminants or surface laitance (a weak dusty layer on concrete). Traces of grease or oil can be removed using Firwood 110 - Cleaning and degreasing fluid. Very smooth concrete or concrete with surface laitance should be treated with Firwood 2709 - Concrete etching fluid to ensure good adhesion (refer to application instructions for correct use of this product). Treated areas should be thoroughly washed down and allowed to dry before coating.
<b>Surface Preparation - Painted Surfaces</b>	Previously painted surfaces should be thoroughly abraded by sanding to improve adhesion and to remove any weak or loose material. It is advisable to test the coating on a small area first to check compatibility with previous coatings
<b>Mixing</b>	Mix thoroughly for approx. 5 mins using a wide bladed stirrer. A wooden batten at least 25mm wide is ideal.
<b>Directions for use</b>	Best results are obtained in warm (minimum 15°C), dry conditions with a good through draught. Mark or mask off the area to be painted. Apply 1 or 2 coats as required at full strength. Do not dilute.  For further information contact our Technical Service Department
<b>Cleaning</b>	Application equipment should be washed immediately after use in clean cold water.
<b>Health &amp; Safety</b>	Refer to Material Safety Data Sheet for information on correct handling and application of this product.

---