

## Rapid dry aluminium paint



Description	A fast drying, brilliant aluminium finish with excellent economical coverage for decorative and protective use on metalwork. Possessing heat resistance up to 250°C.
Recommended Use	Suitable for use on ferrous and non-ferrous metals, wood and other similar absorbent materials. Possesses good heat resistance up to 250°C.
Compliance	For industrial use only . Not for 2004/42 applications
Recommended Application Methods	Conventional spray. Airless spray. Brush.
Colour Range	Aluminium
Physical Properties	<u>VOC Content</u> (as supplied) : max 620g / litre <u>Volume Solids</u> : 30% <u>Mass Solids</u> : 38% <u>Flash Point</u> : 26°C
Drying Time @ 20°C	Surface dry - 10 mins. Hard dry - 1 hour. Overcoat - 1 to 4 hours or 16 hours after application. Do not apply when ambient temperature falls below 3°C or relative humidity exceeds 90%.
Dry Film Thickness	15 - 25 µ
Wet Film Thickness	50 - 85 µ
Theoretical Coverage Rate	15m <sup>2</sup> per litre @ 20µ DFT <i>Coverage rate can be affected by such variables as type and condition of substrate, type of application equipment and individual method of application.</i>
Thinners	Firwood 113 Thinners
Packaging	<u>Pack Size</u> : 5 & 20 litres <u>Weight</u> : 1kg / litre <u>Shelf Life</u> : 2 years from shipment date when stored in unopened, original containers. <u>Storage</u> : Store in temperature range 5-40°C

---

<b>Directions for use</b>	All surfaces should be clean, dry and free from grease, rust, millscale, etc.  Stir well before use but do not apply vigorous or excessive mixing as this could lead to damage to the leafing properties of the paint and consequent loss of brilliance.  For further information contact our Technical Service Department.
<b>Cleaning</b>	Application equipment should be cleaned using Firwood 113 low odour thinners.
<b>Health &amp; Safety</b>	Refer to Material Safety Data Sheet for information on correct handling and application of this product.

---



The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use.